

### Description

**HE125MO** is a polypropylene homopolymer intended for injection moulding. This grade is characterized by good flow properties and high stiffness in and is specially suitable for high-speed injection moulding of articles demanding easy flow.

Its very good organoleptic properties allows this grade to be used with any masterbatch without discoloring problems.

**CAS-No.** 9003-07-0

# **Applications**

House ware and thin wall packaging

Articles with rather long and narrow flow lengths

## **Special Features**

Good flow behaviour High stiffness

### **Physical Properties**

| Property                                   | Typical Value Test Method Data should not be used for specification work |             |  |
|--|--|-------------|--|
| Density                                    | 905 kg/m³  | ISO 1183    |  |
| Melt Flow Rate (230 °C/2,16 kg)            | 12 g/10min   | ISO 1133    |  |
| Flexural Modulus                           | 1.350 MPa  | ISO 178     |  |
| Tensile Modulus (50 mm/min)                | 1.550 MPa  | ISO 527-2   |  |
| Tensile Strain at Yield (50 mm/min)        | 9 %  | ISO 527-2   |  |
| Tensile Stress at Yield (50 mm/min)        | 34 MPa   | ISO 527-2   |  |
| Heat Deflection Temperature (0,45 N/mm²) 1 | 88 °C  | ISO 75-2    |  |
| Charpy Impact Strength, notched (23 °C)    | 3,5 kJ/m²  | ISO 179/1eA |  |

<sup>&</sup>lt;sup>1</sup> Measured on injection moulded specimens acc. to ISO 1873-2

# **Processing Techniques**

This product is easy to process with standard injection moulding machines.

Following moulding parameters should be used as guidelines:

Melt temperature 220 - 260 °C
Holding pressure 200 - 500 bar
Mould temperature 20 - 40 °C
Injection speed High

Minimum to avoid sink marks.

Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters





#### Storage

**HE125MO** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation with resulting odour generation and colour changes.

### Safety

The product is not classified as dangerous.

# Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## **Related Documents**

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet" Recovery and disposal of polyolefins Information on emissions from processing and fires Statement on compliance to food contact regulations





#### **Disclaimer**

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

